


Features

- FloorScore certified no traces of VOCs, phthalate-free, no formaldehyde off-gassing, and are 100% recyclable.
- Patented Välinge® 5G Joint is strongest on the market, and proven to effectively reduce the chances of gapping
- Painted bevels add to a more realistic appearance. Made to closely resemble grout line on tiles
- · Built-in antimicrobial cork underlayment has superior sound absorption and thermal insulation properties
- Armor Care technology: 2-pass UV cured urethane finish that is exceptionally stain and scratch resistant



Armor Care anti-stain and stratch resistant coating

Ultra-thick 0.5mm (20mil) wear layer Beautiful looks with rich texture

High desity composite core, waterproof Cork underlayment - antimicrobial and protects against mould and mildrew

Valinge® 5G locking system





Product Information				
Product Line	SureWood Luxury Vinyl Flooring			
Construction	WPC (wood polymer composite) vinyl			
Dimension	8mm (T) x 305mm (W) x 610mm (L)			
Underlayment	1.5mm antimicrobial cork underlayment			
Wear Layer Thickness	0.5mm (20 mil)			
Finish	2-pass UV cured Urethane Finish			
Installation	Floating installation by clicking the end joints together. Please refer to Installation Instruction			
Warranty	30 Year Residential and 12 Year Commercial Warranty			

Testing						
Classification	Method	Result				
Class	ASTM F1700	Class III, Type B - Embossed				
Slip Resistance	ASTM C1028-07	Dry: 0.80; Wet: 0.71				
Static Load	ASTM F970	Applied Load: 1000 psi, Residual Indentation: 0.04mm				
ΔΙΙC	ASTM E2179-03	23				
IIC	ASTM E492-09	72				
STC	ASTM E90-09	71				
Dimensional Stability	ASTM F2199	Pass: ≤0.02 in. per linear foot				
Resistant to Chemicals	ASTM F925	Pass: Not affected				
Abrasion	ASTM D4060	Test Revolutions: 1000, 0.004% mass loss				
Antibacterial Activity	ASTM G21-15	Pass: No growth observed on specimens				
Reaction to Fire	EN13501-1	Class B fl-s1				
Critical Radiant Flux	ASTM E648	Pass, >0.45 watts/cm ²				
Concentration of Dibutyl Phthalate	ISO 16000	<1 μg/m³ after 28 days				
Concentration of Diethylhexyl Phthalate	ISO 16000	<1 μg/m³ after 28 days				
Flexibility	EN435	No Damage				



Packaging Information								
	Length	Width	Thickness	Sq. ft.	Weight			
	(mm)	(mm)	(mm)	per Carton	(lb. per carton)			
Tile	610	305	8					
Tile Carton	615	310	80	20	32.5			

Pallet Information								
	Length	Width	Height	Volume	# of carton	Sq. ft.	Weight	
	(mm)	(mm)	(mm)	(m³)	per Pallet	/pallet	(lb.)	
Tile Pallet	1225	920	1060	1.19	72	1440	2340	