

## Features

- FloorScore certified no traces of VOCs, phthalate-free, no formaldehyde off-gassing, and are 100% recyclable.
- Patented Välinge® 5G Joint is strongest on the market, and proven to effectively reduce the chances of gapping
- Painted bevels add to a more realistic appearance. Made to closely resemble grout line on tiles
- Built-in antimicrobial cork underlayment has superior sound absorption and thermal insulation properties
- Wear layer is enhanced with Armor Care technology, making it exceptionally stain and scratch resistant

Ultra-thick ( Beautiful lo High densit Cork under

Armor Care anti-stain and scratch resistant coating

Ultra-thick 0.5mm (20mil) wear layer Beautiful looks with rich texture

High density composite core, waterproof Cork underlayment - antimicrobial and protects against mould and mildew

Välinge 5G® locking system



Product Information				
Product Line	SureWood Luxury Vinyl Flooring			
Construction	WPC (wood polymer composite) vinyl			
Dimension	California size: 8.5mm (T) x 225mm (W) x 1830mm (L)			
Underlayment	1.5mm antimicrobial cork underlayment			
Wear Layer Thickness	0.5mm (20 mil)			
Finish	2-pass UV cured Urethane Finish			
Installation	Floating installation by clicking the end joints together. Please refer to Installation Instruction			
Warranty	Lifetime Residential and 12 Year Commercial Warranty			

Testing					
Classification	Method	Result			
Class	ASTM F1700	Class III, Type B - Embossed			
Slip Resistance	ASTM C1028-07	Dry: 0.80; Wet: 0.71			
Static Load	ASTM F970	Applied Load: 1000 psi, Residual Indentation: 0.04mm			
ΔΙΙΟ	ASTM E2179-03	23			
IIC	ASTM E492-09	72			
STC	ASTM E90-09	71			
Dimensional Stability	ASTM F2199	Pass: ≤0.02 in. per linear foot			
Resistant to Chemicals	ASTM F925	Pass: Not affected			
Abrasion	ASTM D4060	Test Revolutions: 1000, 0.004% mass loss			
Antibacterial Activity	ASTM G21-15	Pass: No growth observed on specimens			
Reaction to Fire	EN13501-1	Class B fl-s1			
Critical Radiant Flux	ASTM E648	Pass, >0.45 watts/cm <sup>2</sup>			
Concentration of Dibutyl Phthalate	ISO 16000	<1 µg/m³ after 28 days			
Concentration of Diethylhexyl Phthalate	ISO 16000	<1 µg/m³ after 28 days			
Flexibility	EN435	No Damage			



	Length	Width	Thickness	Sq. ft.	Weight			
	(mm)	(mm)	(mm)	per Carton	(lb. per carton)			
California Size	1830	225	8.5					
California Size Carton	1844	235	56	26.62	47			

## Pallet Information

	Length	Width	Height	Volume	# of carton	Sq. ft.	Weight
	(mm)	(mm)	(mm)	(m³)	per Pallet	/pallet	(lb.)
California Size Pallet	1844	940	830	1.44	52	1384.24	2444